



Russell R. McMurry, P.E., Commissioner
Office of Materials and Testing
15 Kennedy Drive
Forest Park, GA 30297
(404) 608-4700 Main Office

December 5, 2019

Ms. Renee Thomas
Adhesives Technology, Corp.
450 East Copans Road
Pompano Beach, FL 33064

Dear Ms. Thomas:

Subject: Initial Product Evaluation

The Department has approved the following products for use on our construction and maintenance projects. These products will be listed in the Qualified Products List as long as they continue to meet current specifications and perform satisfactorily in the field.

QPL-15 Epoxy Resin Adhesive

<u>Trade Name</u>	<u>Type</u>
Crackbond Healer Sealer	V

The QPL listing will be shown as follows:

Adhesives Technology, Corp.	##/ USA	450 East Copans Road Pompano Beach, FL 33064 www.atcepoxy.com	954-782-2221 800-892-1880	Crackbond Healer Sealer	V	ADHE88605
-----------------------------	------------	--	------------------------------	-------------------------	---	-----------

Products listed in the Qualified Products List (QPL) are subject to a yearly evaluation. Samples will be requested at a later date. The QPL is now available on the Internet at: <http://www.dot.ga.gov/doingbusiness/Materials/qpl/Pages/QPLRequirements.aspx>. We appreciate your interest in marketing products that benefit the Georgia Department of Transportation and the citizens of Georgia.

Sincerely,

Monica L. Flournoy, P.E.
State Materials Engineer

MLF:RD:NC:isr

Enclosure

Georgia Department of Transportation
Office of Materials and Testing
 Epoxy Resin Adhesive

Sample Number:
Site Manager
Sample ID #
Date Received: **Project No:**
County:
Contract ID # **Sample Type:**
Material Code:
Date Sampled: **Sampled From:**
Sampled By: **Examined For::**
Vendor/ Contractor:
Date Completed: **Meets Requirements**
Manufacturer: **Product:**

	Test Results	Minimum	Maximum
Pot Life	<i>29:26 min/sec</i>	10 min/sec	45 min/sec
Bond Strength (24 hr) Reading 1	<i>550 psi</i>	-	-
Bond Strength (24 hr) Reading 2	<i>548 psi</i>	-	-
Bond Strength (24 hr) Reading 3	<i>423 psi</i>	-	-
Bond Strength (24 hr) Average	<i>507 psi</i>	400 psi	-
SAG Test	<i>No SAG</i>	-	-
Shelf Life	<i>24 months</i>	24 months	-

**Results from Inp.Lab Name*

Remarks:
 Lab results for Crackbond Healer Sealer Type- V

State Materials and Test Engineer