

LOW-VISCOSITY, LOW SURFACE TENSION, PENETRATING HEALER/SEALER**PHYSICAL PROPERTIES**

Laboratory Tests	Results
C-881 Viscosity	<40 cps
C-881 Gel Time	50-70 Minutes
C-884 Thermal Compatibility	Pass
D-2240 Shore D Hardness*	68-74
D-570 Absorption*	0.25%
C-882 Bond Strength (2 day cure)	1,500 psi
C-882 Bond Strength (14 day cure)	2,200 psi
C-883 Shrinkage	Pass
D-695 Compressive Modulus*	80,000-120,000 psi
C-695 Compressive Strength*	5,000-5,500 psi
D-2566 Linear Coefficient of Shrinkage*	0.0021
D-638 Tensile Strength*	3,000-3,200 psi
D-638 Tensile Elongation*	35-45%
D-790 Flexural Strength*	3,000-5,000 psi
Percent Solids	75%
VOC Content	<250 g/L
ACI 503R Adhesion to Concrete	>500 psi (concrete failure)
Flash Point	>170F
Specific Gravity	1.04