

10-3792

ONE COMPONENT SEMI-FLEXIBLE EPOXY

DESCRIPTION:

10-3792 is a unique one-component epoxy. It is a single component product which provides shock and impact resistance at elevated temperatures.

TYPICAL SPECIFICATIONS:

Viscosity, 25°C	9,000
Color	Black
Hardness, Shore D	70
Operating Temperature, °C	-50 to +200
Solids Content	100%
Specific Gravity, 25°C	1.4

INSTRUCTIONS FOR USE:

Cure at 120 °C for 2 hours.

PREPARATION OF SURFACES:

Surfaces to be bonded must be clean and grease free. Adhesion can be substantially increased by abrading the surface with a material like emery cloth or sandpaper. A roughened porous surface will produce the best results. Any oxidized metal films should be removed just prior to application of the adhesives.

STORAGE & HANDLING:

The shelf life at 25°C is 6 months in original unopened containers.
The expected shelf life at 0 °C is 1 year.

We recommend refrigerating these adhesives during storage. Extreme warm temperatures during shipping may reduce shelf life. Dry ice or refrigerated shipping is optional and may be requested at the time of order.

Please read the Safety Data Sheet before using this or any other chemical.

AVAILABILITY:

10-3792 is available in a variety of syringe, sizes and styles. It is also available in quarts, gallons, and 5-gallon pails.



IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

08/2024