

# 50-3155

## THERMALLY CONDUCTIVE EPOXY RESIN

### DESCRIPTION:

50-3155 is a highly filled epoxy system with excellent physical, electrical, and thermal properties. 50-3155 offers very high thermal conductivity, excellent electrical insulation, and low thermal expansion. This unique combination of properties makes this system ideal for applications where electrical insulation and mechanical protection must be maintained while transferring heat.

### APPLICATIONS:

50-3155 is ideal for high voltage applications such as power supplies, transformers, high voltage insulators, bushings, etc...

### CHOICE OF CURING AGENTS:

**CATALYST 190:** Room temperature curing with a 45 minute pot life. Tough and rigid at all temperatures up to 150°C.

**CATALYST 140:** Room temperature curing with a 30 minute pot life. Low viscosity and easy handling properties. Excellent adhesion. Has a service temperature up to 150°C (300°F). Will soften slightly above 121°C (250°F).

**CATALYST 30:** Heat curing with a pot life of 4 hours. Low viscosity with excellent handling properties. Excellent thermal and mechanical shock.

### TYPICAL SPECIFICATIONS:

Viscosity @ 25°C (Cat.30) cps	6,000
Viscosity @ 25°C (Cat.190) cps	15,000
Viscosity @ 25°C (Cat.140) cps	5,000
Specific Gravity, 25°C	1.93
Hardness, Shore D	90
Shrinkage, in/in	.003
Elastic Modulus Compressive, psi	$1.5 \times 10^6$
Tensile Strength, psi	8,900
Compressive Strength, psi	16,000
Flexural Strength, psi	13,500
Flexural Modulus, psi	$2.5 \times 10^8$
Izod Impact (ft.-lbs./in)	.35
Water Absorption, 7 Days	.11
Machinability	Poor
Operating Temp. Range °C	-55 to +205
Coefficient of Expansion, /°C	$30 \times 10^{-6}$
Heat Distortion, °C	175
Dielectric Strength, V/mil	560
Dielectric Constant at 60 Hz	6.4
Volume Resistivity, ohm-cm	$4.9 \times 10^{16}$
Dissipation Factor, 60 Hz	.018



## INSTRUCTIONS FOR USE:

Since 50-3155 resin may settle upon storage, remix prior to each use.

### CATALYST 190:

1. By weight, thoroughly mix 5 parts Catalyst 190 to 100 parts 50-3155 resin.
2. Slight warming (40°C) of the resin prior to mixing will improve pourability and air release.
3. Pour and allow to cure overnight or with heat for 2 hours at 66°C (155°F).

### CATALYST 140:

1. By weight, thoroughly mix 9-10 parts Catalyst 140 to 100 parts 50-3155 resin.
2. Slight warming (40°C) of the resin prior to mixing will improve pourability and air release.
3. Pour and allow to cure overnight or with heat for 2 hours at 66°C (155°F).

### CATALYST 30 (Recommended for higher operating temperature and physical property applications):

1. By weight, thoroughly mix 9 parts Catalyst 30 to 100 parts 50-3155 resin.
2. Pour and cure according to one of the following recommended cure schedules:
  - a) 85°C (185°F) 3-4 hours
  - b) 100°C (212°F) 2-3 hoursFor optimum performance, an additional 2 hours @ 365°F (185°C) is recommended.

### IMPORTANT:

**EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS.** The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

07/12