

EPO-TEK[®] **E3001-6**

Technical Data Sheet

For Reference Only

Electrically Conductive, Silver-Filled Epoxy

Date: February 2022 Recommended Cure: 150°C / 1 Hour

Rev: IV

No. of Components: Single Specific Gravity: 2.71 Pot Life: 8 Hours

Shelf Life-Bulk: Six months at -40°C Shelf Life-Syringe: Six months at -40°C

Minimum Alternative Cure(s):

may not achieve performance properties below

150°C / 2 Minutes 130°C / 15 Minutes

NOTE: Container(s) should be kept closed when not in use. Filled systems should be stirred thoroughly before mixing and prior to use. Please see Applications Note available on our website

<u>Product Description:</u> EPO-TEK[®] E3001-6 is a single component, electrically and thermally conductive, snap cure, die attach epoxy. It was designed for JEDEC level IC plastic packaging of semiconductors, hybrid micro-electronics and photonic device assembly. It is a single component version of EPO-TEK[®] E2001-6, shipped in dry ice.

Typical Properties:

To be used as a guide only, not as a specification. Different batches, conditions & applications yield differing results.

Cure condition: 150°C/1 hour * denotes test on lot acceptance basis Data below is not guaranteed.

PHYSCIAL PROPERTIES:

* Color (before cure): Silver

* Consistency Smooth thixotropic paste

* Viscosity (23°C): @ 50 rpm 5,500 - 7,500 cPs

Thixotropic Index: 2.4

* Glass Transition Temp: ≥ 100 °C (Dynamic Cure:20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min)

Coefficient of Thermal Expansion (CTE):

Below Tg: 50×10^{-6} in/in°C **Above Tg:** 106×10^{-6} in/in°C

Shore D Hardness: 83 Lap Shear @ 23°C: 1.159

Die Shear @ 23°C: ≥ 5 Kg 1,700 psi

 Degradation Temp (TGA):
 425 °C

 Weight Loss:
 @ 200°C
 0.17 %

 @ 250°C
 0.20 %

@ 300°C 0.28 % : Continuous: - 55°C to 250°C

OperatingTemp: : Continuous: - 55°C to 250°C Intermittent: - 55°C to 350°C

Storage Modulus: 707,895 psi

lon Content: CI: 103 ppm NA $^{-}$: 14 ppm NH $_{4}^{+}$: 26 ppm K $^{-}$: 1 ppm

* Particle Size: ≤ 20 microns

ELECTRICAL AND THERMAL PROPERTIES:

Thermal Conductivity: 1.54 W/mK

* Volume Resistivity @ 23°C: ≤ 0.0005 Ohm-cm
Volume Resistivity @ 23°C (150°C/5 min cure): 0.002 Ohm-cm

Epoxies and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.

14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805 FAX (978) 663-9782

www.epotek.com



EPO-TEK[®] E3001-6

For Reference Only
Electrically Conductive, Silver-Filled Epoxy

EPO-TEK[®] E2001-6 Advantages & Suggested Application Notes:

- Capable of snap curing at relatively low temperatures, with reasonable pot-life of 8 hours.
- May be purchased frozen in 3cc, 5cc and 10cc syringes.
- Designed for high volume dispensing and syringe rheology. Stamping, pin transfer, printing, or manual methods can be also used.
- Suggested applications:
- ♦ Semiconductor:
 - Snap cure of IC's onto die paddle of lead-frame. Adhesion to Si, Cu, Ag, Au.
 - Fast cure of lead-frames in magazines inside box ovens.
 - Compatible with die size up to 300 mil x 300 mil.
- ♦ Opto-electronics / Photonics packaging:
 - Die attaching laser or photo diode chips for fiber optic modules.
 - Adhesion to surfaces such as Pt, Au, ceramic, kovar, stainless steel, and metallized glass.
 - LED die attach.
 - ITO bonding in LCDs.
- ♦ PCB and general electronic assembly. COB die attach direct onto substrate.
- Increased pot life is available. Contact techserv@epotek.com for your best recommendation.

Epoxies and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.

14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805 FAX (978) 663-9782

www.epotek.com