

20-2121

ELASTOMERIC POTTING & ENCAPSULATING COMPOUND

DESCRIPTION:

20-2121 is formulated for electronic potting, encapsulating and casting applications. The 20-2121 is a two-component, low viscosity, room temperature curing system. This is an easy-to-use product that does not contain TDI, MbOCA or Mercury. 20-2121 will cushion and protect sensitive electronic components. It will impart very little stress on components during cure or thermal cycling.

The base Natural Oil Polyol (NOP) used in 20-2121 is obtained directly from a plant source without chemical modifications. Due to the raw materials selected, this product is low in toxicity and considered a **GREEN** potting compound. Using renewable resources such as NOPs will reduce the demand on non-renewable fossil fuels and reduce the overall production of carbon dioxide.

FEATURES:

- Low Toxicity
- Green
- Low Viscosity
- Low Durometer
- Moisture Resistant
- Low Shrinkage & Exotherm

BENEFITS:

- Reduce employee exposure to dangerous chemicals
- Reduce demand on non-renewable fossil fuels
- Quick self-leveling around components
- Low stress on components & vibration resistant
- Can be used in wet environments
- Will not damage components during cure

TYPICAL PROPERTIES:

| | |
|---------------------------------|-------------|
| Viscosity, 25°C, cps | |
| Polyol | 800 |
| Isocyanate | 20,000 |
| Mixed | 3,200 |
| Mix ratio (Polyol:Iso) | |
| By Volume | 100:94 |
| By Weight | 116:100 |
| Color | Clear/Amber |
| Hardness, Shore A | 65 |
| Operating Temperature Range, °C | -30 to +125 |
| Gel time, Minutes | |
| 25°C | 90 |
| 60°C | 20 |
| Specific gravity @ 25°C | |
| Polyol | 0.96 |
| Isocyanate | 1.14 |

| | |
|--------------------------------------|-----------------------|
| Elongation, % | 155 |
| Tensile strength, psi | 2,000 |
| Tear strength, PLI | 119 |
| Coefficient of thermal expansion, °C | 2.10×10^{-4} |
| Linear shrinkage, in./in. | 0.014 |
| Thermal conductivity, W/m-K | 0.3 |
| Dielectric strength, V/mil | 650 |
| Volume resistivity, ohm-cm | 7.2×10^{14} |
| Surface resistivity, 25°C, ohm | $>1.0 \times 10^{15}$ |
| Dielectric constant, 1 kHz | 3.4 |
| Dissipation Factor, 1 kHz | 0.017 |

Note: When cured at room temperature full hardness and final properties are achieved in 7-10 days.

INSTRUCTIONS FOR USE:

1. By weight, thoroughly mix 100 parts Isocyanate to 116 parts Polyol according to mix ratio provided in the above table. Two components should be carefully weighed in metal, plastic or glass containers. Avoid using paper cups and wooden stirrers.
2. Mixed material can be degassed at 29 in Hg to ensure bubble free castings. Containers should be large enough to allow frothing.
3. Cure according to one of the following cure schedules:
 - a) 25°C 24 Hours
 - b) 45°C 2.5 Hours
 - c) 65°C 1.5 Hours
 - d) 85°C 40 Minutes

STORAGE & HANDLING & SAFETY:

Store both components at 75-85°F in original containers. If the containers are opened and the contents partially used, the material left in the container should be blanketed with dry nitrogen before sealing.

Please read the Safety Data Sheet before using this or any other chemical.

PACKAGING:

This product is available in quarts, gallons, 5-gallon pails and 55-gallon drums.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

10/2017



epoxies.com

21 Starline Way
Cranston, RI 02921 USA

t 401.946.5564

f 401.946.5526