

20-1715 Firm, Extended Cure, Potting and Encapsulating Silicone Gel

DESCRIPTION:

20-1715 is a firm, clear silicone elastomeric gel, designed for electronic potting applications.

20-1715 offers excellent electrical properties, and its soft cushioning provides vibration and thermal shock protection. It's outstanding at providing protection from moisture, dust and other environmental contaminants.

Due to its excellent electrical properties, dielectric strength, and resistivity 20-1715 is used to encapsulate electronic components, junction boxes, power modules and LED's.

20-1715 is formulated without solvents or other toxic materials, and is not regulated or considered hazardous for transportation.

20-1715 is part of the 20-1700 series of potting and encapsulating silicone gels.

FEATURES:

• Simple to use

• Low toxicity

- Easy 1:1 mix ratio
- Soft
- Easy to penetrate and remove
- Solvent free
- Fast cure

Improves productivity
Extends life of electronic assemblies

Low stress on components and vibration resistant

Repairs or removal of components saves money

Excellent electrical properties
 External

TYPICAL SPECIFICATIONS:

Viscosity, 25°C, cps	
Resin (Part A)	6,500
Activator (Part B)	6,000
Mix Ratio, (Resin:Activator)	
By Volume	1:1
By Weight	1:1
Color	
Resin (Part A)	Clear
Activator (Part B)	Clear
Hardness, Shore A	Firm Gel
Operating Temperature Range, °C	-55 to +200
Pot Life, 25°C, 100 grams	20 minutes
Specific Gravity, 25°C	
Resin (Part A)	0.98
Activator (Part B)	0.98

epoxies.com

21 Starline Way Cranston, RI 02921 USA t 401.946.5564 f 401.946.5526



Thermal Conductivity, W/m-K	0.16
Volume Resistivity, ohm-cm, 25°C	1 x 10 ¹⁵
Dielectric Constant, 60 Hz	2.7
Dielectric Strength, kV/mil	18

INSTRUCTIONS FOR USE:

- 1. By weight or volume, mix 1 part base silicone to 1 part activator. Mix uniformly, scrap sides and bottom of mixing container. Do not whip air into mixture.
- 2. De-air by pulling vacuum on mixed material.
- 3. Apply mixed material and follow one of the cure schedules
 - a) 25°C 12 hours
 - b) 60°C 10 minutes

SUBSTRATE NOTES:

Certain materials may inhibit the cure of this product. Materials that should be avoided include sulfur containing materials, nitrogen containing materials (i.e. amines) some silicones (tin cured), and butyl and chlorinated rubbers. If in doubt, a patch test should be done.

STORAGE, HANDLING & SAFETY:

When stored in the original, unopened container, in a dry location at 25°C, 20-1715 has a shelf life of approximately 12 months.

Please read the Safety Data Sheet before using this or any other chemical.

AVAILABILITY:

Using the popular TriggerBond® cartridges will add convenience and reliability. 20-1715 is available in quart, gallon, 5-gallon pail, and 55-gallon drums. It is also available in the popular TriggerBond® 50ml, 200ml, and 400ml cartridges.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/2025

epoxies.com 21 Starline Way Cranston, RI 02921 USA t 401.946.5564 f 401.946.5526