



Product Information Sheet

EPO-TEK® EV2118-2

Date: February 2022
Rev: IX
No. of Components: Two
Mix Ratio by Weight: 1 : 1
Specific Gravity: Part A: 2.53 Part B: 3.33
Pot Life: 3 Days
Shelf Life- Bulk: One year at room temperature
Shelf Life- Syringe: One year at -40°C

Recommended Cure: 150°C / 1 Hour

Minimum Alternative Cure(s):
May not achieve performance properties listed below
150°C / 10 Minutes
120°C / 15 Minutes
100°C / 1 Hour

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

Product Description: A silver-filled, electrically conductive epoxy designed for semiconductor and electronic assembly.

Typical Properties: Cure condition: varies as required Different batches, conditions & applications yield differing results.

Data below is not guaranteed. To be used as a guide only, not as a specification. * denotes test on lot acceptance basis

PHYSICAL PROPERTIES:

* Color (before cure):	Part A: Shiny silver	Part B: Shiny silver
* Consistency:	Smooth paste	
* Viscosity (23°C) @ 100 rpm:	1,500 - 3,000	cPs
Thixotropic Index:	4.4	
* Glass Transition Temp:	≥ 40	°C (Dynamic Cure: 20-200°C/ISO 25 Min; Ramp -40-200°C @20°C/Min)
Shore A Hardness:	55	
Lap Shear @ 23°C:	428	psi
Die Shear @ 23°C:	≥ 5	Kg 1,778 psi
Degradation Temp:	325	°C
Weight Loss:		
	@ 200°C:	0.61 %
	@ 250°C:	0.84 %
	@ 300°C:	1.58 %
Suggested Operating Temperature:	< 250	°C (Intermittent)
Storage Modulus:	130,977	psi
* Particle Size:	≤ 20	microns

ELECTRICAL AND THERMAL PROPERTIES:

Thermal Conductivity:	4.0	W/mK
* Volume Resistivity @ 23°C:	≤ 0.0005	Ohm-cm

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.

14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782

www.epotek.com