



50-3345 RESIN

DESCRIPTION:

50-3345 thermally conductive flexible epoxy formulation is designed for applications that require low stress during cure and electrical insulation.

50-3345 is a low viscosity system that is most commonly used for potting and encapsulating power supplies, transformers, regulators, motors, capacitors, batteries, coils etc. This system is excellent in applications that require a compound to remain flexible for long term aging. This system has a low peak exotherm, making it ideal for large castings.

The 50-33345 resin and catalyst is sold in convenient quart kits, gallon kits, 5 gallon pails, and 55 gallon drums.

TYPICAL SPECIFICATIONS:

Color	Black
Mix Viscosity @ 25°C, cps	
Resin	12,000
Catalyst	60
Mixed	2,000
Pot Life, 100 gram mass @ 25°C	2 Hrs.
Specific Gravity, 25°C	1.52
Hardness, Shore A	50
Operating Temp. Range, °C	-65 to +135
Dielectric Strength, V/mil	475
Dielectric Constant at 60 Hz	3.75
Volume Resistivity, ohm cm at 25°C	1.5×10^{15}
Dissipation Factor, 60 Hz	.015
Thermal Conductivity, W/m- °K	1.01

INSTRUCTIONS FOR USE:

1. Agitate 50-3345 Resin thoroughly to re-disperse fillers. Some settling during transit or storage is common.
2. Mix 100 parts 50-3345 Resin to 20 parts 50-3345 Catalyst by weight
3. Cure at room temperature 24 hours or for 1-2 hours at 65°C.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

03/2022

epoxies.com

21 Starline Way
Cranston, RI 02921 USA

t 401.946.5564

f 401.946.5526