

40-3905

ELECTRICALLY CONDUCTIVE EPOXY ADHESIVE AND COATING

DESCRIPTION:

40-3905 is an electrically conductive epoxy system designed for applications requiring low temperature cures. 40-3905 will cure at room temperature in 18-24 hours or can be accelerated with mild heat.

This is a solvent free epoxy system filled with pure silver. It has outstanding adhesion to plastics, aluminum, copper, magnesium, steel, bronze, nickel, kovar, ceramic, glass, phenolic, and printed circuit boards. 40-3905 can also be thinned with up to 10% Toluol for many coating applications.

FEATURES:

- Electrically conductive
- Thermally conductive
- Room temperature cure
- Good bond strength

TYPICAL SPECIFICATIONS:

Viscosity, 25°C, cps	
Mixed	Thixotropic paste
Mix ratio, (Resin:Hardener)	
By Weight	100:5
Color	Silver
Hardness, Shore D	80-85
Operating Temperature Range, °C	-60 to +135
Pot life, 100 grams, 25°C	45 Minutes
Specific Gravity, 25°C	
Resin	2.98
Hardener	1.0
Linear shrinkage, in/in	0.003
Tensile lap shear, psi (Al to Al)	1,200
Flexural strength, psi	10,900
Thermal conductivity, W/m-K	8.65
Thermal expansion coefficient, 1/°C	26x10 ⁻⁶
Volume resistivity, ohm-cm	1.0x10 ⁻⁴

**INSTRUCTIONS FOR USE:**

1. All surfaces to be bonded or coated should be completely cleaned and grease free.
2. By weight thoroughly mix 5 parts 40-3905 Catalyst to 100 parts 40-3905 Resin (pre-weighed kits eliminate the need to weigh components).
3. For coating applications thin with Toluol.
4. Cure according to one of the following cure Schedules:

a) 25°C	18-24 Hours
b) 65°C	2-3 Hours

STORAGE, HANDLING & SAFETY:

40-3905 Resin and hardener should be stored at 25°C in original tightly sealed containers. Expected shelf life is twelve months in original unopened containers.

Filler settling is common with these products. Gently stir resin and hardener before using to make sure fillers are evenly dispersed.

Please read the Safety Data Sheet before using this or any other chemical.

AVAILABILITY:

40-3905 is available in 3-dram vials and 1 oz, 2oz, and 8oz containers.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/2025