

POLYURETHANE POTTING & ENCAPSULATING RESINS

THE GREEN SERIES

20-2101 Enterable Gel

20-2160 Shore A 60

20-2180 Shore A 80

DESCRIPTION:

This series of polyurethane systems is engineered for electronic potting, encapsulating, and casting applications. They are low in viscosity, low in toxicity and available in the popular TriggerBond® dual barrel cartridge dispensing system. These elastomeric systems are suitable for a variety of electronic insulating applications. The durometers range from an enterable gel to Shore A 80. 20-2183 is a faster gelling version of 20-2180 that can be demolded in 1 hour.

GREEN:

The base Natural Oil Polyol (NOP) used in these systems is obtained directly from a plant source without chemical modifications. Renewable resources, like NOP's, reduce the demand on non-renewable fossil fuels and the overall production of carbon dioxide.

FEATURES:

- Green
- Low Viscosity
- Available in TriggerBond®
- Low Durometer
- Moisture Resistant
- Convenient Mix Ratios
- Low Shrinkage & Exotherm

BENEFITS:

- Reduce demand on non-renewable fossil fuels
- Quick self leveling around components
- Easy to use packaging
- Low stress on components & vibration resistant
- Can be used in wet environments
- Easy to process by hand or with meter mix
- Less stress to components during cure

TYPICAL PROPERTIES:

	<u>20-2101</u>	<u>20-2160</u>	<u>20-2180</u>
Viscosity, cps, 25°C			
Polyol Resin	1,500	1,500	2,000
Isocyanate	3,000	13,000	2,500
Mixed	1,600	2,500	1,700
Available Colors	Clear	Clear, Black	Clear, Black
Hardness, Shore A	Gel	60	80
Mix Ratio (Iso:Polyol)			
By Volume	1:4	1:2	1:2
By Weight	25:100	55:100	60:100
Operating Temp. Range, °C	-55 to +125	-55 to +125	-55 to +125
Pot Life, Minutes, 25 °C	20	20	20

	<u>20-2101</u>	<u>20-2160</u>	<u>20-2180</u>
Specific Gravity, 25° C			
Polyol Resin	0.97	1.03	0.97
Isocyanate	1.15	1.13	1.15
Elongation	N/A	150	220
Tear Strength, pli	N/A	40	80
Tensile Strength, psi	N/A	375	1700
Dielectric Constant, 1 KHz	4.0	3.6	3.4
Dissipation Factor, 1 KHz	0.017	0.017	0.017
Dielectric Strength, V/mil	625	625	650
Surface Resistivity, ohm, 25°C	1.0 x 10 ¹⁵	1.0 x 10 ¹⁵	1.0 x 10 ¹⁵
Volume Resistivity, ohm-cm	7.2 x 10 ¹⁴	7.2 x 10 ¹⁴	7.2 x 10 ¹⁴
Coefficient of Thermal Expansion, ppm/°C	200	200	200
Thermal Conductivity, W/m·°K	0.3	0.3	0.3

Note: When cured at room temperature final properties are achieved in 7-10 days.

INSTRUCTIONS FOR USE:

1. By weight, thoroughly mix according to mix ratio above. Two components should be carefully weighed in metal, plastic, or glass containers. Avoid using paper cups and wooden stirrers. If using TriggerBond® cartridges follow dispensing guidelines.
2. Mixed material can be degassed at 1 to 5 mm Hg to ensure bubble free castings. Containers should be large enough to allow frothing.
3. Cure according to one of the following cure schedules:

a) 25 °C for 24 Hours	c) 65 °C for 1.5 Hours
b) 45 °C for 2.5 Hours	d) 85 °C for 40 Minutes

STORAGE, HANDLING, & SAFETY:

Store both components at 25 °C. If the containers are opened and the contents partially used, the material left in the container should be blanketed with dry nitrogen before sealing. The expected shelf life is 12 months in the bulk containers and 6 months in TriggerBond®.

Please read the Safety Data Sheet before using this or any other chemical.

AVAILABILITY:

These products are available in the convenient TriggerBond® dual barrel cartridges (50 mL, 200 mL, and 400 mL), quarts, gallons, five-gallon pails and 55-gallon drums.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.