



20-2150

POLYURETHANE POTTING & ENCAPSULATING RESIN

DESCRIPTION:

This polyurethane system is engineered for electronic potting, encapsulating, and casting applications. It is low in viscosity and low in toxicity.

GREEN:

The base Natural Oil Polyol (NOP) used in this system is obtained directly from a plant source without chemical modifications. Using renewable resources, such as NOP's, will reduce the demand on non-renewable fossil fuels and reduce the overall production of carbon dioxide.

FEATURES:

- Green
- Low Viscosity
- Low Durometer
- Moisture Resistant
- Convenient Mix Ratio
- Low Shrinkage & Exotherm

BENEFITS:

Reduce demand on non-renewable fossil fuels
Quick self leveling around components
Low stress on components & vibration resistant
Can be used in wet environments
Easy to process by hand or with meter mix
Less stress to components during cure

TYPICAL PROPERTIES:

Viscosity, 25°C, cps	
Polyol Resin	1,500
Isocyanate	5,500
Mixed	2,500
Mix Ratio (Polyol:Iso)	
By Weight	2:1
Color	Black
Hardness, Shore A	50
Operating Temperature range, °C	-30 to +125
Gel Time, 25°C, Minutes	20
Specific gravity, 25°C	
Polyol Resin	1.03
Isocyanate	1.13
Elongation, %	150
Tensile strength, psi	375
Tear strength, psi	40
Coefficient of thermal expansion, °C	2.00 x 10 ⁻⁴
Thermal conductivity, W/m-K	0.3



Dielectric strength, V/mil	625
Volume resistivity, ohm-cm	7.2×10^{14}
Dielectric constant, 1 kHz	3.6
Dissipation Factor, 1 kHz	0.017

Note: When cured at room temperature full hardness and final properties are achieved in 7-10 days.

INSTRUCTIONS FOR USE:

1. By weight, thoroughly mix according to mix ratio provided in the above table. Two components should be carefully weighed in metal, plastic or glass containers. Avoid using paper cups and wooden stirrers.
2. Mixed material can be degassed at 29 in Hg to ensure bubble free castings. Containers should be large enough to allow frothing.
3. Cure according to one of the following cure schedules:
 - a) 25°C 24 Hours
 - b) 45°C 2.5 Hours
 - c) 65°C 1.5 Hours
 - d) 85°C 40 Minutes

STORAGE & HANDLING & SAFETY:

Store both components at 75-85°F in original containers. If the containers are opened and the contents partially used, the material left in the container should be blanketed with dry nitrogen before sealing.

Please read the Safety Data Sheet before using this or any other chemical.

AVAILABILITY:

This product is available in quarts, gallons, 5-gallon pails and 55-gallon drums.

IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/2025