

# 20-1700 Soft, Fast Cure, Potting and Encapsulating Silicone Gel

# **DESCRIPTION:**

20-1700 is a soft, clear silicone elastomeric gel, designed for electronic potting applications.

20-1700 offers excellent electrical properties, and its soft cushioning provides vibration and thermal shock protection. It's outstanding at providing protection from moisture, dust and other environmental contaminants.

Due to its excellent electrical properties, dielectric strength, and resistivity 20-1700 is used to encapsulate electronic components, junction boxes, power modules and LED's.

20-1700 is formulated without solvents or other toxic materials, and is not regulated or considered hazardous for transportation.

# **FEATURES:**

- Easy 1:1 mix ratio
- Soft
- Easy to penetrate and remove
- Solvent free
- Fast cure
- Excellent electrical properties

## **BENEFITS:**

- Simple to use
- Low stress on components and vibration resistant
- Repairs or removal of components saves money
- Low toxicity
- Improves productivity
- Extends life of electronic assemblies

0.16

## TYPICAL SPECIFICATIONS:

Thermal Conductivity, W/m-K

Viscosity, 25°C, cps	
Resin (Part A)	6,500
Activator (Part B)	6,500
Mix Ratio, (Resin:Activator)	
By Volume	1:1
By Weight	1:1
Color	
Resin (Part A)	Clear
Activator (Part B)	Clear
Hardness, Shore A	Soft Gel
Operating Temperature Range, °C	-55 to +200
Pot Life, 25°C, 100 grams	6 minutes
Specific Gravity, 25°C	
Resin (Part A)	0.98
Activator (Part B)	0.98
, ,	



Volume Resistivity, ohm-cm, 25°C	1 x 10 <sup>15</sup>
Dielectric Constant, 60 Hz	2.7
Dielectric Strength, kV/mil	18

# **INSTRUCTIONS FOR USE:**

- 1. By weight or volume, mix 1 part base silicone to 1 part activator. Mix uniformly, scrap sides and bottom of mixing container. Do not whip air into mixture.
- 2. De-air by pulling vacuum on mixed material.
- 3. Apply mixed material and follow one of the cure schedules

a) 25°Cb) 60°Cb minutes

#### **SUBSTRATE NOTES:**

Certain materials may inhibit the cure of this product. Materials that should be avoided include sulfur containing materials, nitrogen containing materials (i.e. amines) some silicones (tin cured), and butyl and chlorinated rubbers. If in doubt, a patch test should be done.

## STORAGE, HANDLING & SAFETY:

When stored in the original, unopened container, in a dry location at 25°C, 20-1700 has a shelf life of approximately 12 months.

Please read the Safety Data Sheet before using this or any other chemical.

#### **AVAILABILITY:**

Using the popular TriggerBond® cartridges will add convenience and reliability. Due to their extremely short Pot Life, TriggerBond® packaging or Meter Mix Dispense Equipment is strongly recommended for 20-1700.

20-1700 is available in quart, gallon, 5-gallon pail, and 55-gallon drums. It is also available in the popular TriggerBond® 50ml, 200ml, and 400ml cartridges.

## IMPORTANT:

EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS. The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

06/2025