

Date: April 2026
No. of Components: Single
Specific Gravity: 1.15
Pot Life: < 20 Hours
Shelf Life- Syringe: Six months at -40°C

Rev: IV

Recommended Cure	
Initial Tack 100 mW/cm ² @ 240-365nm	10 sec.
followed by 150°C	30 min.
Alternative Thermal Cures (After Initial Tack)	
100°C	30 min.
80°C	1 hour
* Contact Technical Services for application-specific variations	

NOTES:

- To prevent gelation, keep containers away from light sources.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

Product Description: EPO-TEK[®] HYB-353ND-LV is a single component, high temperature hybrid epoxy for semiconductor, fiber optic and medical applications. It is designed to have similar cured performance to EPO-TEK[®] 353ND, modified to allow for initial UV tacking. It is a lower viscosity version of EPO-TEK[®] HYB-353ND.

Typical Properties: Cure condition: Initial Tack 100mW/cm² for 10 seconds @ 240-365nm + 150°C/30 Minutes

To be used as a guide only, not as a specification. Different batches, conditions & applications yield differing results.

*denotes test on lot acceptance basis Data below is not guaranteed.

PHYSICAL PROPERTIES:

* Color (before cure):	Light Yellow
* Consistency:	Pourable liquid
* Viscosity (23°C) @ 100 rpm:	800 - 2,000 cPs
* Glass Transition Temp:	≥ 80 °C (Dynamic Cure:20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min)
Coefficient of Thermal Expansion (CTE):	
Below Tg:	46 x 10 ⁻⁶ in/in°C
Above Tg:	137 x 10 ⁻⁶ in/in°C
Shore D Hardness:	83
Die Shear:	≥ 15 Kg 5,334 psi
Degradation Temp:	400 °C
Weight Loss:	
@ 200°C	0.08 %
@ 250°C	0.58 %
@ 300°C	1.61 %
Suggested Operating Temperature:	< 350 °C (Intermittent)

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:	≥ 50% @ 550 nm
	≥ 95% @ 1,100-1,600 nm
	≥ 98% @ 800-1,000 nm
Refractive Index (uncured):	1.5215 @ 589 nm

Epoxyes and Adhesives for Demanding Applications™

SELLER MAKES NO OTHER WARRANTY OR GUARANTEE OF ANY KIND REGARDING FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. BUYER ASSUMES FULL RESPONSIBILITY FOR QUALITY CONTROL, TESTING AND DETERMINATION OF SUITABILITY OF PRODUCT FOR ITS INTENDED APPLICATION OR USE.

EPOXY TECHNOLOGY, INC.

14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782

www.epotek.com